



# DOWLEX™ 2517

The Dow Chemical Company - Polyethylene Resin

Wednesday, December 1, 2021

## General Information

### Product Description

DOWLEX™ 2517 Polyethylene Resin is a narrow molecular weight distribution copolymer designed to offer good ESCR and low temperature properties with excellent flexibility. This resin has good processability over a wide range of molding conditions.

- Linear Low Density Polyethylene
- For lids, housewares and containers
- Excellent low temperature flexibility, good ESCR

Complies with:

- U.S. FDA FCN 424
- Canadian HPFB No Objection (With Limitations)
- EU, No 10/2011
- U.S. FDA-DMF
- U.S. USP 23
  - Consult the regulations for complete details.

### General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• North America	
Additive	• Antiblock: No	• Processing Aid: No	• Slip: No
Agency Ratings	• DMF • EU No 10/2011	• FDA FCN 424 • HPFB (Canada) No Objection <sup>1</sup>	• USP 23
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>2</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	0.919	0.919	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25 g/10 min	25 g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (ESCR)			ASTM D1693
122°F (50°C), 100% Igepal, F50	4.00 hr	4.00 hr	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength			ASTM D638
Yield	1400 psi	9.65 MPa	
Break	1300 psi	8.96 MPa	
Tensile Elongation			ASTM D638
Yield	3.0 %	3.0 %	
Break	600 %	600 %	
Flexural Modulus - 2% Secant	34000 psi	234 MPa	ASTM D790B
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Impact Strength <sup>3</sup>	190 ft-lb/in <sup>2</sup>	399 kJ/m <sup>2</sup>	ASTM D1822
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	45	45	ASTM D2240

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

# DOWLEX™ 2517

## The Dow Chemical Company - Polyethylene Resin

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	103 °F	39.4 °C	ASTM D648
Brittleness Temperature	< -105 °F	< -76.1 °C	ASTM D746
Vicat Softening Temperature	197 °F	91.7 °C	ASTM D1525
Melting Temperature (DSC)	255 °F	124 °C	Internal Method
Peak Crystallization Temperature (DSC)	218 °F	103 °C	Internal Method

### Additional Information

Plaque molded and tested in accordance with ASTM D4976.

### Notes

<sup>1</sup> With limitations

<sup>2</sup> Typical properties: these are not to be construed as specifications.

<sup>3</sup> Type S