



Lustran® PG298

INEOS Styrolution - Acrylonitrile Butadiene Styrene

Thursday, December 21, 2023

General Information

Product Description

Lustran® PG298 resin is a grade of ABS (acrylonitrile butadiene styrene) for use in automotive and general-purpose applications. It provides a unique combination of flow and rigidity, with increased scratch resistance.

FEATURES

- SAE J1685: ABS0111
- Plating grade
- Improved thermocycle performance
- Outstanding plate adhesion
- Increased scratch resistance

APPLICATIONS

- Grills
- Wheel covers
- Mirror housings
- Appliance, lawn and garden

General

Material Status	• Commercial: Active		
Regional Availability	• Latin America	• North America	
Features	• General Purpose	• Good Adhesion	• Good Scratch Resistance
Uses	• Appliances • Automotive Applications	• General Purpose • Lawn and Garden Equipment	
Agency Ratings	• SAE J1685		
Automotive Specifications	• CHRYSLER MS-DB-197 CPN2220 Color: Natural • DAIMLER TRUCK 48-25358-003 • DELPHI DX300010 • FORD WSK-M4D806-A	• FORD WSK-M4D836-A • FORD WSS-M4D827-A3 • GM GMP.ABS.007 • GM GMW15572P-ABS-T1 Color: Q258	• GM GMW15572P-ABS-T5 • HONDA HES C251-06 A-3-M • SAE J1685 ABS0141
Processing Method	• Injection Molding		

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

Lustran® PG298

INEOS Styrolution - Acrylonitrile Butadiene Styrene

ASTM & ISO Properties ¹			
Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06	ASTM D792
Melt Mass-Flow Rate (MFR)			ISO 1133
220°C/10.0 kg	19 g/10 min	19 g/10 min	
230°C/3.8 kg	5.0 g/10 min	5.0 g/10 min	
Molding Shrinkage	0.40 to 0.70 %	0.40 to 0.70 %	ISO 294-4
Water Absorption			ISO 62
Saturation, 73°F (23°C)	1.0 %	1.0 %	
Equilibrium, 73°F (23°C), 50% RH	0.22 %	0.22 %	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress (Yield, 73°F (23°C))	7250 psi	50.0 MPa	ISO 527-2
Tensile Strain (Yield, 73°F (23°C))	2.8 %	2.8 %	ISO 527-2
Flexural Modulus (73°F (23°C))	392000 psi	2700 MPa	ISO 178
Films	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus - MD	2800 psi	19.3 MPa	ISO 527-3
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	4.8 ft·lb/in ²	10 kJ/m ²	
73°F (23°C)	10 ft·lb/in ²	22 kJ/m ²	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load ²			
66 psi (0.45 MPa), Annealed	216 °F	102 °C	ISO 75-2/B
264 psi (1.8 MPa), Annealed	210 °F	99.0 °C	ISO 75-2/A
Vicat Softening Temperature	208 °F	98.0 °C	ISO 306/B50
CLTE - Flow	4.4E-5 to 6.1E-5 in/in/°F	8.0E-5 to 1.1E-4 cm/cm/°C	ISO 11359-2
Thermal Conductivity	1.2 Btu·in/hr/ft ² /°F	0.17 W/m/K	ISO 8302

Processing Information			
Injection	Typical Value (English)	Typical Value (SI)	
Drying Temperature	176 °F	80 °C	
Drying Time	4.0 hr	4.0 hr	
Rear Temperature	473 to 491 °F	245 to 255 °C	
Middle Temperature	482 to 500 °F	250 to 260 °C	
Front Temperature	491 to 509 °F	255 to 265 °C	
Processing (Melt) Temp	500 to 536 °F	260 to 280 °C	
Mold Temperature	122 to 140 °F	50 to 60 °C	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 4 h/80 °C

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.