

Technical Data

Product Description

Silicone Rubber, LSR

Molded Parts, Food Contact, Plastics and Rubber Processing
 Molded Seals, Plastics and Rubber Processing
 Molded Parts, Technical, Plastics and Rubber Processing
 Vibration Dampers, Automotive & Transportation
 Molded Parts, Automotive, Plastics and Rubber Processing

General

Material Status	• Commercial: Active		
UL Yellow Card ¹	• E75704-101062596 • E75704-249839		
Search for UL Yellow Card	• Wacker Chemie AG		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Food Contact Acceptable	• General Purpose	
Uses	• Automotive Applications • Automotive Under the Hood	• Gaskets • Membranes	• Seals • Valves/Valve Parts
Processing Method	• Injection Molding • Liquid Injection Molding (LIM)		

Uncured Properties	Nominal Value (English)	Nominal Value (SI)	Test Method
Color	Clear/Transparent	Clear/Transparent	
Density	1.16 g/cm ³	1.16 g/cm ³	ISO 1183
Viscosity	710 Pa·s	710 Pa·s	DIN 53019
Cured Properties	Nominal Value (English)	Nominal Value (SI)	Test Method
Shore Hardness (Shore A)	76	76	DIN 53505
Tensile Strength	1160 psi	8.00 MPa	DIN 53504
Tensile Elongation at Break	210 %	210 %	DIN 53504
Compression Set	13 %	13 %	DIN ISO 815-B
Tear Strength	103 lbf/in	18.0 kN/m	ASTM D624B
Rebound Resilience	69 %	69 %	DIN 53512
Electric Strength	580 V/mil	23 kV/mm	DIN IEC 243
Dissipation Factor (50 Hz)	2.0E-4	2.0E-4	DIN VDE 0303

Notes

¹ A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

² Typical properties: these are not to be construed as specifications.

