



# Lustran® 433

## INEOS Styrolution - Acrylonitrile Butadiene Styrene

Thursday, December 21, 2023

### General Information

#### Product Description

Lustran® 433 is a general-purpose injection molding grade of ABS (Acrylonitrile Butadiene Styrene). It is a high impact, high-gloss ABS, available only in natural (NR) and black (BK904000).

#### FEATURES

- High impact strength
- High gloss
- UL 94 HB rated

#### APPLICATIONS

- Housings
- Toys
- Small appliances
- Consumer goods

#### General

Material Status	• Commercial: Active		
Regional Availability	• Latin America	• North America	
Features	• General Purpose	• High Gloss	• High Impact Resistance
Uses	• Appliances • Consumer Applications	• General Purpose • Housings	• Toys
Appearance	• Black	• Natural Color	
Processing Method	• Injection Molding		

### ASTM & ISO Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Melt Mass-Flow Rate (MFR)			ASTM D1238
220°C/10.0 kg	12 g/10 min	12 g/10 min	
230°C/3.8 kg	3.6 g/10 min	3.6 g/10 min	
Molding Shrinkage - Flow	4.0E-3 to 6.0E-3 in/in	0.40 to 0.60 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	370000 psi	2550 MPa	ASTM D638
Tensile Strength (Yield, 73°F (23°C))	6100 psi	42.1 MPa	ASTM D638
Tensile Elongation (Break)	30 %	30 %	ASTM D638
Flexural Modulus (73°F (23°C))	380000 psi	2620 MPa	ASTM D790
Flexural Strength (5.0% Strain)	10500 psi	72.4 MPa	ASTM D790

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.

# Lustran® 433

## INEOS Styrolution - Acrylonitrile Butadiene Styrene

Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
-40°F (-40°C)	1.2 ft·lb/in	64 J/m	
73°F (23°C)	7.0 ft·lb/in	370 J/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Rockwell Hardness (R-Scale)	109	109	ASTM D785
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	197 °F	91.7 °C	
66 psi (0.45 MPa), Annealed	211 °F	99.4 °C	
264 psi (1.8 MPa), Unannealed	185 °F	85.0 °C	
264 psi (1.8 MPa), Annealed	202 °F	94.4 °C	
CLTE - Flow	5.0E-5 in/in/°F	9.0E-5 cm/cm/°C	ASTM D696
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	175 °F	79 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Mold Temperature	110 to 150 °F	43 to 66 °C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Copyright ©, 2023, Formerra, LLC. All the information in this literature is for general information purpose only. Formerra makes no representations, guarantees, or warranties of any kind with respect to the information contained in this literature, including its accuracy, completeness, reliability, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for pricing, property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Formerra makes no warranties or guarantees respecting suitability of either Formerra's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. FORMERRA MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature or any other provided literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner. Any action you take upon the information you find in this literature is strictly at your own risk. Formerra will not be liable for any losses and/or damages in connection with the use of this literature. By using this literature, you hereby consent to this disclaimer and agree to its terms.